

Amendments to the Specification:

Please amend the paragraph at page 6, line 10, as follows:

Articles, such as mouse pads or coaster, in which the entire top surface of the article is covered with the flocking can be produced on a continuous basis, as shown in FIGS. 3 and 5. Rolls 21, 23, and 25 of a flocked release sheet 1, the hot melt film 13, and the substrate 15 are provided. The three parts are brought together at a laminating station 33. Rollers can be provided in front of the station 33 so that the three elements are adjacent each other as they enter the laminating station. In the laminating station, heat and pressure are applied to the three sheets (the flocked release sheet, the hot melt film, and the substrate) to melt the hot melt film. The melted hot melt film will then cure or cross-link, as noted above, to adhere the flock to the substrate. A web 35 exits the laminating station. The web 35 is then allowed to cool. The web 35 is ultimately directed to a cutting station where it is cut into individual articles. Once the web 35 is cooled, it can be directed immediately to a cutting station (after the sheet 35 cools), or can it can be wound up on an uptake roller to be cut into individual articles at a later time, or at a different location. At the cutting station, the release sheet 3 is removed from the flock and gathered on an uptake roll or is otherwise disposed of. After the release sheet has been removed from the flock, the substrate with the flock adhered thereto is cut to form the articles 11. It is also likely that one could remove the release liner either before or after the die cutting procedure. As shown in FIG. 3, a fringe material 50 can be ~~applied to~~ located on a pair of opposing peripheral edges of the ~~flocked release sheet 1 or substrate 15 during this manufacturing process~~ article 11.